



**ARMOROC PANEL | Cement Bonded Particle Board (CBPB)**

<b>DOUBLE SPAN LOADING CONDITION</b>				
<b>( FOR PANELS SPANNING TWO SPANS )</b>				
<b>Uniformly Distributed Loads - Lbs per square foot</b>				
<b>Span: Center-to-center of supports (inches)</b>				
<b>ARMOROC PANEL THICKNESS</b>	<b>LOAD GOVERNED BY *</b>	<b>12"</b>	<b>16"</b>	<b>24"</b>
8mm (5/16")	L/360 ▲ limit between supports	43	24	9*
	L/240 ▲ limit between supports	43	24	10
10mm (3/8")	L/360 ▲ limit between supports	67	37	16
	L/240 ▲ limit between supports	67	37	16
12mm (1/2")	L/360 ▲ limit between supports	97	54	24
	L/240 ▲ limit between supports	97	54	24
16mm (5/8")	L/360 ▲ limit between supports	172	97	43
	L/240 ▲ limit between supports	172	97	43
19mm (3/4")	L/360 ▲ limit between supports	243	136	60
	L/240 ▲ limit between supports	243	136	60
22mm (7/8")	L/360 ▲ limit between supports	326	183	81
	L/240 ▲ limit between supports	326	183	81
25mm (1")	L/360 ▲ limit between supports	421	237	105
	L/240 ▲ limit between supports	421	237	105
28mm (1-1/8")	L/360 ▲ limit between supports	528	297	132
	L/240 ▲ limit between supports	528	297	132
32mm (1-1/4")	L/360 ▲ limit between supports	690	388	172
	L/240 ▲ limit between supports	690	388	172
38mm (1-1/2")	L/360 ▲ limit between supports	973	547	243
	L/240 ▲ limit between supports	973	547	243

\* Values marked with an asterisk ( \* ) are governed by the corresponding deflection ratio. All other load values are governed by a bending strength value of 9 N/mm<sup>2</sup> (1,305 psi), which is the minimum allowable performance requirement of the EN 634-2 European Standard for CBPB. ARMOROC<sup>®</sup> performance against the EN 632-2 shall be considered superior.

<sup>1</sup> If ARMOROC<sup>®</sup> panels are allowed to become saturated, reduce live load working capacity by approximately 30% until panels have re-dried. All load data remains valid for re-dried panels.

<sup>2</sup> A safety factor of 4 was applied during the preparation of the data presented in this table.

<sup>3</sup> Weight of panel and flooring must be subtracted from table values to calculate live load capacity.

<sup>4</sup> Values in this table generated by Progressive Engineering Inc., PEI Project No. 2007-1708-1, using an average shear strength of 1,308 psi from Bodycote test report No. 06-06-M0351 Revision 3, Table 24.

<sup>5</sup> All ARMOROC<sup>®</sup> installations must be designed and reviewed by a qualified architect or engineer. Panels perpendicular to supports. Refer to installation specifications for additional information.

**Ameriform, LLC., 162 Cook Ln., Marlborough, MA 01752**  
**Ph: (508)485-9812 | Fx: (508)251-3084 | www.ameriformllc.com**

